

ПАРАМЕТРЫ ТРАФАРЕТНЫХ СЕТОК ASADA

ИЗ НЕРЖАВЕЮЩЕЙ СТАЛИ



#	Номер [нит/дюйм]	Номер [нит/см]	Диаметр нити [мм]	Внутр. размер ячейки [мм]	Открытое пространство	Толщина некаландр. [мкм]	Толщина каландр. 1 [мкм]	Толщина каландр. 2 [мкм]	Толщина каландр. 3 [мкм]
MS-730/13	730	287	0.013	0.022	39%	28 ± 2	20 ± 1	18 ± 1	15 ± 1
HS-D 650/14	650	256	0.014	0.025	41%	34 ± 2			23 ± 2
MS-640/15	640	252	0.015	0.025	39%	35 ± 2	25 ± 1	21 ± 1	17 ± 1
BS-500/16	500	197	0.016	0.035	47%	36 ± 2	25 ± 2	20 ± 1	16 ± 1
BS-500/19	500	197	0.019	0.032	39%	41 ± 2	30 ± 2	25 ± 1	19 ± 1
MS-500/16	500	197	0.016	0.035	47%	36 ± 2	25 ± 2	20 ± 1	15 ± 1
MS-500/19	500	197	0.019	0.032	39%	41 ± 2	36 ± 2	25 ± 1	20 ± 1
HS-R-500/13	500	197	0.013	0.038	55%	29 ± 3	24 ± 2	21 ± 1	17 ± 1
HS-D 500/19	500	197	0.019	0.032	39%	45 ± 2			25 ± 1
SHS-430/13	430	169	0.013	0.046	61%	29 ± 3	24 ± 2	21 ± 1	17 ± 1
BS-400/19	400	157	0.019	0.045	49%	39 ± 2	34 ± 2	30 ± 1	23 ± 1
BS-400/23	400	157	0.023	0.041	41%	55 ± 2	40 ± 2	35 ± 1	25 ± 1
BS-400/25	400	157	0.025	0.039	37%	57 ± 2	49 ± 2	40 ± 1	30 ± 1
MS-400/19	400	157	0.019	0.045	49%	42 ± 2	30 ± 2	23 ± 1	18 ± 1
MS-400/23	400	157	0.023	0.041	41%	55 ± 2	40 ± 2	35 ± 1	26 ± 1
SHS-R-400/16	400	157	0.016	0.048	56%	36 ± 3	25 ± 2	21 ± 1	15 ± 1
3D-400-66	400	157	0.023	0.041	41%	66 ± 3			
SHS-380/14	380	150	0.014	0.053	62%	32 ± 2	26 ± 2	20 ± 1	14 ± 1
SHS-360/16	360	142	0.016	0.055	60%	36 ± 3	32 ± 2	21 ± 1	16 ± 1
HS-360/16	360	142	0.016	0.055	60%	36 ± 3	32 ± 2	20 ± 1	16 ± 1
HS-D 360/25	360	142	0.025	0.046	42%	59 ± 2		41 ± 2	29 ± 1
BS-325/28	325	128	0.028	0.050	41%	62 ± 2	55 ± 2	47 ± 1	40 ± 1
BS-325/30	325	128	0.030	0.048	38%	62 ± 2	60 ± 2	47 ± 2	42 ± 1
MS-325/24	325	128	0.024	0.054	48%	51 ± 2	44 ± 2	38 ± 2	25 ± 1
MS-325/28	325	128	0.028	0.050	41%	56 ± 2	51 ± 2	45 ± 2	39 ± 2
SHS-325/16	325	128	0.016	0.062	63%	35 ± 3	32 ± 2	20 ± 1	18 ± 1
HS-325/16	325	128	0.016	0.062	63%	35 ± 2	32 ± 2	20 ± 1	17 ± 1
3D-325-77	325	128	0.028	0.050	41%	75 ± 3			
S4-325-112	325	128	0.028	0.050	41%	112 ± 5			
S5-325-134	325	128	0.028	0.050	41%	134 ± 5			
BS-300/30	300	118	0.030	0.055	42%	68 ± 2	59 ± 2	50 ± 2	45 ± 1
SHS-290/20	290	114	0.020	0.068	60%	45 ± 3	36 ± 2	30 ± 1	20 ± 1
HS-290/20	290	114	0.020	0.068	60%	45 ± 2	36 ± 2	30 ± 1	20 ± 1
BS-270/35	270	106	0.035	0.059	39%	77 ± 2	70 ± 2	58 ± 2	40 ± 2
BS-250/30	250	98	0.030	0.072	50%	62 ± 2	58 ± 2	50 ± 2	45 ± 2
BS-250/35	250	98	0.035	0.067	43%	78 ± 2	64 ± 2	57 ± 2	55 ± 2
BS-250/40	250	98	0.040	0.062	37%	90 ± 3	86 ± 2	72 ± 2	67 ± 2
MS-250/30	250	98	0.030	0.072	50%	62 ± 2	58 ± 2	45 ± 2	28 ± 2
HS-250/20	250	98	0.020	0.082	65%	44 ± 2	37 ± 2	30 ± 1	18 ± 1
HS-D 250/35	250	98	0.035	0.067	43%	—			44 ± 1
3D-250-85	250	98	0.030	0.072	50%	83 ± 4			
S5-250-141	250	98	0.030	0.072	50%	141 ± 5			
HS-230/25	230	91	0.025	0.085	60%	55 ± 2	40 ± 2	30 ± 2	27 ± 1
BS-200/40	200	79	0.040	0.087	47%	82 ± 3	77 ± 2	72 ± 2	63 ± 2
3D-200-115	200	79	0.040	0.087	47%	112 ± 4			
S4-200-174	200	79	0.040	0.087	47%	174 ± 5			
S5-200-190	200	79	0.040	0.087	47%	190 ± 5			
3D-165-126	165	65	0.045	0.109	50%	124 ± 5			

#	Номер [нит/дюйм]	Номер [нит/см]	Диаметр нити [мм]	Внутр. размер ячейки [мм]	Открытое пространство	Толщина некаландр. [мкм]	Толщина каландр. 1 [мкм]	Толщина каландр. 2 [мкм]	Толщина каландр. 3 [мкм]
3D-120-165	120	47	0.060	0.152	51%	165 ± 5			
3D-80-225	80	32	0.080	0.238	56%	225 ± 5			

Дополнительная информация:
<https://www.agalsea.ru/brand/asada/>

